

45 Shore A red / grey

The high quality red /grey, composite vulcanized natural membrane. The membrane can be supplied with a smooth or cloth finish. Membrane has high tear strength, high elongationat break and outstanding heat ageing properties.



Area of application:

The membrane has been specially developed for use in membrane presses in the wood industry. Foil, veneer and others.

Technical data

Type	NR-RG-2	NR-RG-2.5	NR-RG-3	NR-RG-4
Thickness, mm:	2	2.5	3	4
Width, mm:	1600 / 2000	1600 / 2000	1600 / 2000	1600 / 2000
Length, m:	16	16	16	16
Working temperature, max C:	120	120	120	120
Tensile strength, Mpa:	60	60	60	60
Hardness, Shore A:	45 +/- 3	45 +/- 3	45 +/- 3	45 +/- 3
Elasticity, %:	650	650	650	650
Tear strength, N/mm ² :	20	20	20	20
Color:	Red / Grey	Red / Grey	Red / Grey	Red / Grey
Surface:	Smooth / Cloth	Smooth / Cloth	Smooth / Cloth	Smooth / Cloth