

42 Shore A Grey

The high quality, gray, vulcanized natural rubber sheet. The high tear strength, high elongation at break and outstanding heat ageing properties.



Area of application:

The membrane has been specially developed for use in membrane presses in the wood industry. Foil, veneer and others.

Technical data

Type	NR-2	NR-2.5	NR-3	NR-4
Thickness, mm:	2	2.5	3	4
Width, mm:	1600 / 2000	1600 / 2000	1600 / 2000	1600 / 2000
Length, m:	16	16	16	16
Working temperature, max C:	130	130	130	130
Tensile strength, Mpa:	60	60	60	60
Hardness, Shore A:	42 +/- 3	42 +/- 3	42 +/- 3	42 +/- 3
Elasticity, %:	700	700	700	700
Tear strength, N/mm ² :	20	20	20	20
Color:	Grey	Grey	Grey	Grey
Surface:	Smooth	Smooth	Smooth	Smooth