


55 Shore A

High resistance to tearing, dynamic tension and compression loads.

High temperature resistance
Excellent elasticity
Long-term flexibility

Area of application:

Foil, veneer, mineral materials and others.



Technical data

Type	SM55-3
Thickness, mm:	3
Thickness tolerance, mm:	+/- 0,4
Width, mm:	1660
Length, m:	12
Density, g/cm ³ :	1,16 +/- 0,02
Working temperature, max C:	240
Tensile strength, Mpa:	8,5
Hardness, Shore A:	55 +/- 5
Elasticity, %:	650
Tear strength, N/mm ² :	9,3
Color:	Grey
Surface:	Smooth